



JDG Series AGM-GEL battery

6-EVF-180


General Features

- Nanosilica colloidal electrolyte and high tin positive plate alloy design to enhance battery performance
- Relatively rich electrolyte, high temperature and low temperature performance is superior
- Long cycle life, excellent deep cycle discharge ability
- Excellent charge acceptance ability
- Precision sealing technology
- Long life



Dimension: 533(L) × 207(W) × 215(H) × 218(TH)

Unit: mm



Terminal Dimensions

Specification	
Nominal Voltage	12V
Nominal Capacity	190Ah@10hour-rate to 1.80V per cell @25°C
Design life	10 years
Terminal	M8
Approx. Weight	Approx 53.5kg ±3% (118±3%lbs)
Container Material	ABS (UL94-HB, UL94-V0 Optional)
short-circuit current	2400A
Internal resistance(Full charged at 25°C:)	5.0 mΩ
Self discharge	3% of capacity declined per month at 25°C
Operating Temperature	
Discharge:	-20 ~50°C(-4~ 122°F)
Charge :	-20 ~50°C(-4~ 122°F)
Storage:	-20 ~50°C(-4~ 122°F)
Charge Method(25 °C)	
Charge current:	Max. 47.5A; Recom. 19A
Float charge: 13.5-13.8V	recom. 13.8V(-18mV/ °C)
Equalize charge: 13.8-14.1V	recom. 14.1V(-24mV/ °C)
Cycle charge: 14.4-15.0V	recom. 14.7V(-30mV/ °C)

Standards

Executive standard: IEC 60896-21/22,
GB/T 19638.1-2014

Applications

- UPS/EPS
- Power systems
- Telecommunications system
- Emergency lighting, Auto control system
- Solar/wind generating storage cyclic
- Motive Power Applications

Rated Capacity

10Hour Rate (19.0A to 10.8V)	190.0Ah
3Hour Rate (50.5A to 10.2V)	151.5Ah
1Hour Rate (120.2A to 9.6V)	120.2Ah

Attain Certificate




Disclaimer: Manufacturers have the right to self-modify the parameters of the product updates, please keep in touch with manufacturers to obtain the latest information.




JDG Series AGM-GEL battery

6-EVF-180


Discharge characteristic




Charging characteristic



The effect of temperature on capacity



The effect of temperature on float life



Constant Current Discharge Characteristics Unit: A (25°C, 77°F)

FV/Time	15min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.60V	333.1	201.8	150.8	120.2	89.3	71.2	53.6	43.2	36.7	31.2	24.1	20.0	10.5
1.65V	319.9	193.8	144.8	115.5	86.6	69.6	51.9	41.8	35.8	30.8	23.8	19.8	10.3
1.70V	299.7	185.2	138.4	110.6	83.2	66.7	50.5	40.9	34.9	30.1	23.5	19.5	10.2
1.75V	278.9	175.2	132.2	107.2	79.8	64.4	49.0	39.8	34.0	29.4	23.1	19.2	10.2
1.80V	262.6	170.5	127.5	102.5	76.0	62.4	48.5	38.7	33.1	28.5	22.7	19.0	10.1
1.85V	217.9	144.3	111.3	90.1	68.7	55.2	42.6	35.1	30.1	26.0	21.3	17.5	9.65

Constant Power Discharge Characteristics Unit: W/cell (25°C, 77°F)

FV/Time	15min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.60V	585.0	366.6	274.4	220.1	165.2	131.1	101.1	80.9	69.1	60.0	47.0	39.4	20.6
1.65V	567.6	355.6	265.6	213.8	161.1	128.9	99.6	79.0	67.6	59.4	46.6	39.0	20.3
1.70V	539.6	343.3	262.4	208.2	158.8	124.7	95.4	77.1	66.0	58.2	46.0	38.4	20.1
1.75V	509.4	331.5	251.6	203.7	154.4	121.4	94.8	75.4	64.6	56.9	45.5	38.0	20.1
1.80V	481.8	320.1	242.1	195.3	146.4	119.4	92.3	74.6	63.1	55.9	44.8	37.5	19.9
1.85V	401.5	278.4	215.1	174.5	136.0	109.2	82.8	68.6	59.1	51.1	42.1	35.4	18.8