



JPC Series lead-Carbon battery

JPC6-200


General Features

- Lead-carbon composite negative plate, both capacitance and battery characteristics
- Long cycle life, excellent deep cycle discharge ability
- Excellent charge acceptance ability
- Optimized capability of instant high-current discharging
- Strong high and low temperature performance
- Precision sealing technology



Dimension:260(L)×180(W) ×268(H)×273(TH)

Unit: mm



Terminal Dimensions

Specification

Nominal Voltage	6V
Nominal Capacity	200Ah
Design life	15 years
Terminal	M8
Approx. Weight	Approx32.5kg (72.8lbs)
Container Material	ABS
Self discharge	3% of capacity declined per month at 25°C

Rated Capacity

10Hour Rate (23.0A to 10.5V)	230.0Ah
3Hour Rate (67.0A to 10.5V)	201.0Ah
1Hour Rate (174A to 10.5V)	174.0Ah

Operating Temperature

Discharge:	-20 ~50°C(-4~ 122°F)
Charge :	-20 ~50°C(-4~ 122°F)
Storage:	-20 ~50°C(-4~ 122°F)

Charge Method(25 °C)

Max charge current	33.0A
Float Use:	6.75-6.90V@25
Cycle Use :	7.20-7.50V@25

Standards

Executive standard :GB/T32620-2016

Applications


- Solar/ wind energy and other new energy storage
- Hybrid vehicles, electric bicycles and other new energy vehicles
- Other backup or cycle purposes

Attain Certificate




Disclaimer: Manufacturers have the right to self-modify the parameters of the product updates, please keep in touch with manufacturers to obtain the latest information.


Discharge characteristic




Charging characteristic



The effect of temperature on capacity



The effect of discharge depth on cycle life



Constant Current Discharge Characteristics Unit: A (25°C, 77°F)

FV/Time	30min	1h	2h	3h	5h	8h	10h	20h
1.60V	302	179	92.7	69.5	45.3	28.1	23.7	12.7
1.65V	296	178	92.1	68.9	45.1	27.8	23.5	12.6
1.70V	290	177	91.3	67.8	44.5	27.6	23.2	12.6
1.75V	288	174	90.0	67.0	44.0	27.3	23.0	12.5
1.80V	276	170	88.4	66.7	42.9	27.3	22.8	12.4
1.85V	251	157	83.9	62.9	40.8	26.1	22.1	12.2

Constant Power Discharge Characteristics Unit: W/cell (25°C, 77°F)

FV/Time	30min	1h	2h	3h	5h	8h	10h	20h
1.60V	546	340	175	132	86.1	54.7	45.5	25.1
1.65V	540	337	174	131	85.6	54.1	45.0	25.0
1.70V	540	334	174	130	85.0	53.9	44.5	24.9
1.75V	537	331	173	129	84.5	53.6	44.3	24.8
1.80V	523	328	172	129	83.4	53.1	43.8	24.6
1.85V	479	304	165	122	79.7	51.4	43.0	24.4