



Electric vehicle battery expert 6 - EVF-62






General Features

- High corrosion resistant performance: Pb-Ca multi-alloy grid
- High energy density and power density
- Optimized capability of instant high-current discharging
- Excellent charge acceptance ability
- Strong high and low temperature performance
- Low self-discharge rate



Dimension:223(L)×150(W) ×177(H)×177(TH)

Unit: mm



Specification

Nominal Voltage	12V
Nominal Capacity	62Ah@3Hour-rate to 1.75V per cell @25℃
Design life	5 years
Terminal	M6
Approx. Weight	Approx16.8kg±3% (37.04lbs±3%)
Container Material	ABS
Self discharge	3% of capacity declined per month at 25℃

Rated Capacity

20Hour Rate (3.80A to 10.5V)	76.0Ah
5Hour Rate (13.4A to 10.5V)	67.0Ah
3Hour Rate (20.67A to 10.5V)	62.0Ah

Operating Temperature

Discharge:	-20 ~50℃(-4~ 122°F)
Charge :	-20 ~50℃(-4~ 122°F)
Storage:	-20 ~50℃(-4~ 122°F)

Charge Method(25 °C)

Max charge current	9.3A
Float Use:	13.7-13.9V@25
Cycle Use :	14.7-14.9V,@25

Standards

Executive standard :GB/T32620-2016

Applications

- Electric vehicle
- Electric wheelchair
- Electric scooter
- Electric play car for children
- Garbage truck
- Patrol car


Attain Certificate




Disclaimer: Manufacturers have the right to self-modify the parameters of the product updates, please keep in touch with manufacturers to obtain the latest information.




Discharge characteristic




Charging characteristic



The effect of temperature on capacity



The effect of discharge depth on cycle life



Constant Current Discharge Characteristics Unit: A (25°C, 77°F)

FV/Time	30min	1h	2h	3h	5h	8h	10h	20h
1.60V	81.0	52.2	30.9	21.28	13.8	8.93	7.53	3.85
1.65V	79.4	51.9	30.8	21.18	13.7	8.85	7.46	3.84
1.70V	77.9	51.6	30.4	20.78	13.6	8.77	7.39	3.82
1.75V	77.2	50.8	30.0	20.67	13.4	8.70	7.32	3.80
1.80V	73.9	49.5	29.5	20.47	13.1	8.70	7.25	3.78
1.85V	67.5	45.9	28.0	19.36	12.4	8.29	7.03	3.71

Constant Power Discharge Characteristics Unit: W/cell (25°C, 77°F)

FV/Time	30min	1h	2h	3h	5h	8h	10h	20h
1.60V	146.4	99.2	58.3	40.7	26.2	17.38	14.53	7.63
1.65V	144.3	98.4	58.1	40.1	26.1	17.18	14.33	7.60
1.70V	144.3	97.6	57.9	39.9	25.9	17.08	14.13	7.56
1.75V	143.3	96.7	57.5	39.6	25.8	17.08	14.13	7.53
1.80V	140.3	95.7	57.3	39.5	25.5	16.87	13.92	7.49
1.85V	129.1	88.9	54.9	37.6	24.3	16.36	13.72	7.42